This Page Is Inserted by IFW Operations and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

As rescanning documents will not correct images, please do not report the images to the Image Problem Mailbox.

CLAIMS

1	Claim 1. In a process for producing an olefin by the vapor
2	phase oxidative dehydrogenation of alkane having from 2 to 5
3	carbon atoms in the presence of molecular oxygen, the
4	improvement comprising, carrying out the vapor phase oxidative
5	dehydrogenation in the presence of an oxidative dehydrogenation
6	catalyst comprising a multimetal mixed oxide having the formula
7	$\mathbf{M}\mathbf{n}_{\alpha}\mathbf{E}^{1}{}_{\beta}\mathbf{E}^{2}{}_{\mathbf{Y}}\mathbf{O}_{\mathbf{x}}\tag{1}$
8	where Mn denotes manganese;
9	O denotes oxygen;
10	E ¹ represents one or more metal elements selected from the
11	group consisting of phosphorus, arsenic, antimony, boron, sulfur,
12	selenium, tellurium, fluorine, chlorine, bromine, iodine, niobium,
13	tantalum, tungsten, rhenium and copper;
14	E² represents one or more metal elements selected from the
15	group consisting of chromium, iron, cobalt, nickel, silver, gold, zinc,
16	thallium, tin, lead, bismuth, lithium, sodium, potassium, rubidium,
17	cesium, magnesium, calcium, strontium, barium, yttrium, lanthanum
18	cerium, neodymium, and samarium; and,
19	α , β , γ and x denote atomic numbers of Mn, E^1 , E^2 , and oxygen
20	respectively, and,
21	when $\alpha = 1$, $\beta = 0.01-10$, $\gamma = 0-5$, and x has a numerical value
22	determined by the state of oxidation of the elements other than
23	oxygen.
1	Claim 2. The process according to claim 1, wherein, in the
2	oxidative dehydrogenation catalyst of formula (1), when $\alpha=1$,
3	$\beta = 0.02-2$ and $\gamma = 0-1$.

1	Claim 3. The process according to claim 2, wherein E ¹
2	comprises at least sulfur, and the sulfur is added in the form of its
3	sulfate ion (SO ₄ 2).
1	Claim 4. The process according to claim 1, wherein E ¹
2	comprises at least sulfur, and the sulfur is added in the form of its
3	sulfate ion (SO ₄ 2).
1	Claim 5. The process according to claim 1, wherein the
2	oxidative dehydrogenation catalyst of formula (1) is one which is
3	dried and fired at temperatures not higher than 300°C.
1	Claim 6. The process according to claim 1, wherein the
2	oxidative dehydrogenation catalyst is supported on a refractory
3	inorganic carrier.
1	Claim 7. The process according to claim 1, wherein the
2	oxidative dehydrogenation of said alkane is carried out at a space
3	velocity of from 300 to 30,000 hr ⁻¹ , and at a temperature of from 250
4	to 650 °C.
1	Claim 8. The process according to claim 1, wherein the
2	oxidative dehydrogenation catalyst is selected from the group
3	consisting of
4	$Mn_1Sb_{0.15}O_x$, $Mn_1Sb_{0.25}O_x$, $Mn_1B_{0.1}O_x$, $Mn_1S_{0.1}O_x$, $Mn_1Nb_{0.05}O_x$, $Mn_1W_{0.05}O_x$,
5	$Mn_1Re_{0.05}O_x$, $Mn_1Cu_{0.1}O_x$, $Mn_1Cl_{0.4}O_x$, $Mn_1Sb_{0.15}Cr_{0.1}O_x$, $Mn_1Sb_{0.15}Na_{0.1}O_x$,
6	$Mn_1Sb_{0.15}Mg_{0.1}O_x$, $Mn_1Sb_{0.15}Ce_{0.1}O_x$, $Mn_1S_{0.15}Cr_{0.1}O_x$, $Mn_1Cl_{0.4}Sn_{0.1}O_x$
7	$Mn_1Sb_{0.15}W_{0.05}Cr_{0.1}O_x$, $Mn_1Sb_{0.15}W_{0.05}S_{0.15}Cr_{0.1}O_x$, and
8	$Mn_1Sb_{0.15}W_{0.05}Nb_{0.05}Cr_{0.1}O_x$.
1	Claim 9. In a process for producing unsaturated aldehyde and
2	unsaturated acid by the vapor phase oxidative dehydrogenation of
3	C_2 to C_5 alkene in the presence of molecular oxygen, the
4	improvement comprising, carrying out the vapor phase oxidative

3

sulfate ion (SO_4^2).

, . . . t

5 dehydrogenation in the presence of an oxidative dehydrogenation 6 catalyst comprising a multimetal mixed oxide having the formula 7 $Mn_{\alpha}E^{1}_{\beta}E^{2}_{\nu}Ox$ (1) 8 where Mn denotes manganese: 9 O denotes oxygen; E¹ represents one or more metal elements selected from the 10 group consisting of phosphorus, arsenic, antimony, boron, sulfur, 11 12 selenium, tellurium, fluorine, chlorine, bromine, iodine, niobium. 13 tantalum, tungsten, rhenium and copper; 14 E² represents one or more metal elements selected from the group consisting of chromium, iron, cobalt, nickel, silver, gold, zinc, 15 thallium, tin, lead, bismuth, lithium, sodium, potassium, rubidium, 16 17 cesium, magnesium, calcium, strontium, barium, yttrium, lanthanum, 18 cerium, neodymium, and samarium; and, 19 α , β , γ and x denote atomic numbers of Mn, E^1 , E^2 , and oxygen, 20 respectively, and, 21 when $\alpha = 1$, $\beta = 0.01-10$, $\gamma = 0-5$, and x has a numerical value determined by the state of oxidation of the elements other than 22 23 oxygen. 1 Claim 10. The process according to claim 9, wherein, in the 2 oxidative dehydrogenation catalyst of formula (1), when $\alpha = 1$, $\beta =$ 3 0.02-2 and y = 0-1. 1 Claim 11. The process according to claim 10, wherein E¹ 2 comprises at least sulfur, and the sulfur is added in the form of its 3 sulfate ion (SO_a^2). Claim 12. The process according to claim 9, wherein E¹ 1 comprises at least sulfur, and the sulfur is added in the form of its 2

Claim 13. The process according to claim 9, wherein the 1 2 oxidative dehydrogenation catalyst of formula (1) is one which is 3 dried and fired at temperatures not higher than 300°C. 1 Claim 14. The process according to claim 9, wherein the 2 oxidative dehydrogenation catalyst is supported on a refractory inorganic carrier. 3 $\sqrt[3]{\text{Claim 15.}}$ The process according to claim 9, wherein the 4 oxidative dehydrogenation of said alkene is carried out at a space 5 6 velocity of from 300 to 30,000 hr⁻¹, and at a temperature of from 7 250 to,650 °C. Claim 16. The process according to claim 9, wherein the 8 oxidative dehydrogenation catalyst of formula (1) is a catalyst of 9 10 the following formula (2): 11 $Mo_aBi_bFe_cA_dB_eC_fD_aO_x$ (2),12 wherein Mo denotes molybdenum, Bi denotes bismuth, Fe 13 denotes iron, O denotes oxygen, A represents at least one metal element selected from the 14 15 group consisting of cobalt and nickel, B represents at least one metal element selected from the 16 group consisting of alkali metals and thallium, 17 C represents at least one metal element selected from the 18 19 group consisting of silicon, aluminum, zirconium and titanium, D represents at least one metal element selected from the 20 group consisting of tungsten, phosphorus, tellurium, antimony, 21 tin, cerium, lead, niobium, manganese, arsenic and zinc, 22 23 a, b, c, d, e, f, g, and x represent the atomic ratios of the 24 respective elements, and, when a = 12, b = 0.1-10, c = 0.1-20, d = 2-20, 25 e = 0.001 = 10, f = 0.30, g = 0.4, and x is a numerical value 26 determined by the state of oxidation of the elements other than 27 oxygen.

1	! Claim 17. In a process for producing unsaturated acid having
2	from 2 to 5 carbon atoms, by the vapor phase oxidative
3	dehydrogenation of the corresponding unsaturated aldehyde of
4	from 2 to 5 carbon atoms, in the presence of molecular oxygen,
5	the improvement comprising, carrying out the vapor phase
6	oxidative dehydrogenation in the presence of an oxidative
7	dehydrogenation catalyst comprising a multimetal mixed oxide
8	having the formula
9	$Mn_{\alpha}E^{1}{}_{\beta}E^{2}{}_{\gamma}Ox \qquad \qquad (1)$
10	where Mn denotes manganese;
11	O denotes oxygen;
12	E ¹ represents one or more metal elements selected from the
13	group consisting of phosphorus, arsenic, antimony, boron, sulfur,
14	selenium, tellurium, fluorine, chlorine, bromine, iodine, niobium,
15	tantalum, tungsten, rhenium and copper;
16	E ² represents one or more metal elements selected from the
17	group consisting of chromium, iron, cobalt, nickel, silver, gold,
18	zinc, thallium, tin, lead, bismuth, lithium, sodium, potassium,
19	rubidium, cesium, magnesium, calcium, strontium, barium
20	yttrium, lanthanum, cerium, neodymium, and samarium; and,
21	α , β , γ and x denote atomic numbers of Mn, E^1 , E^2 , and
22	oxygen, respectively, and,
23	when $\alpha = 1$, $\beta = 0.01-10$, $\gamma = 0-5$, and x has a numerical value
24	determined by the state of oxidation of the elements other than
25	oxygen.
1	Claim 18. The process according to claim 17, wherein the
2	oxidative dehydrogenation catalyst is represented by the
3	following formula (3):
4	$MO_hV_iW_jE_kF_iG_mH_nO_x (3)$
5	where Mo denotes molybdenum, V denotes vanadium, W
6	denotes tungsten, O denotes oxygen,

17

18

.

E represents at least one element selected from the group 7 consisting of copper, cobalt, bismuth and iron, 8 9 F represents at least one element selected from the group 10 consisting of antimony and niobium, G represents at least one element selected from the group 11 consisting of silicon, aluminum, zirconium, and titanium, 12 H represents at least one element selected from the group 13 14 consisting of alkaline earth metals, thallium, phosphorus, tellurium, tin, cerium, lead, manganese and zinc; 15 h, i, j, k, l, m, n, and x represent the atomic ratios of the 16 respective elements, and, when h=12, i=0.1-10, j=0-10, k=0.1-20, 17 l=0.10, m=0.10, n=0.30, and x has a numerical value determined 18 by the state of oxidation of the elements other than oxygen. 19 Claim 19. A process for producing unsaturated acid by the 1 vapor phase oxidative dehydrogenation of C₂ to C₅ alkene in the 2 3 presence of molecular oxygen, which comprises, oxidatively dehydrogenating lower alkene of from 2 to 5 carbon atoms in the 5 vapor phase in the presence of oxidative dehydrogenation catalyst comprising a multimetal mixed oxide having the formula 6 7 $Mn_{\alpha}E^{1}_{\beta}E^{2}_{\gamma}O_{\gamma}$ (1) 8 where Mn denotes manganese; 9 O denotes oxygen; E¹ represents one or more metal elements selected from the 10 group consisting of phosphorus, arsenic, antimony, boron, sulfur, 11 12 selenium, tellurium, fluorine, chlorine, bromine, iodine, niobium, 13 tantalum, tungsten, rhenium and copper; 14 E² represents one or more metal elements selected from the group consisting of chromium, iron, cobalt, nickel, silver, gold, 15 zinc, thallium, tin, lead, bismuth, lithium, sodium, potassium, 16

rubidium, cesium, magnesium, calcium, strontium, barium

yttrium, lanthanum, cerium, neodymium, and samarium; and,

20

17	α , β , γ and λ denote atomic numbers of wit, ϵ , ϵ , and
20	oxygen, respectively, and,
21	when $\alpha=$ 1, $\beta=$ 0.01-10, $\gamma=$ 0-5, and x has a numerical value
22	determined by the state of oxidation of the elements other than
23	oxygen, to produce a mixture of unsaturated aldehyde and
24	unsaturated acid, and
25	subjecting the unsaturated aldehyde to further vapor phase
26	oxidative dehydrogenation in the presence of oxidative
27	dehydrogenation catalyst of formula (1) to produce the
28	corresponding unsaturated acid.
1	Claim 20. The process according to claim 19, wherein the
2	oxidative dehydrogenation catalyst used in the oxidative
3	dehydrogenation of said unsaturated aldehyde is represented by
4	the following formula (3):
5	$MO_{n}V_{i}W_{j}E_{k}F_{l}G_{m}H_{n}O_{x} $ (3)
6	where Mo denotes molybdenum, V denotes vanadium, W
7	denotes tungsten, O denotes oxygen,
8	E represents at least one element selected from the group
9	consisting of copper, cobalt, bismuth and iron,
10	F represents at least one element selected from the group
11	consisting of antimony and niobium,
12	G represents at least one element selected from the group
13	consisting of silicon, aluminum, zirconium, and titanium,
14	H represents at least one element selected from the group
15	consisting of alkaline earth metals, thallium, phosphorus,
16	tellurium, tin, cerium, lead, manganese and zinc;
17	h, i, j, k, l, m, n, and x represent the atomic ratios of the
18	respective elements, and, when $h=12$, $i=0.1-10$, $j=0-10$, $k=0.1-20$,
19	I=0-10, $m=0-10$, $n=0-30$, and x has a numerical value determined

by the state of oxidation of the elements other than oxygen.

1	Claim 21. The process according to claim 20, wherein the
2	oxidative dehydrogenation catalyst used for the oxidative
3	dehydrogenation of said alkene to produce said mixture is a
4	catalyst of the following formula (2):
5	$MO_aBi_bFe_cA_dB_eC_fD_gO_x$ (2),
6	wherein Mo denotes molybdenum, Bi denotes bismuth, Fe
7	denotes iron, O denotes oxygen,
8	A represents at least one metal element selected from the
9	group consisting of cobalt and nickel,
10	B represents at least one metal element selected from the
11	group consisting of alkali metals and thallium,
12	C represents at least one metal element selected from the
13	group consisting of silicon, aluminum, zirconium and titanium,
14	D represents at least one metal element selected from the
15	group consisting of tungsten, phosphorus, tellurium, antimony,
16	tin, cerium, lead, niobium, manganese, arsenic and zinc,
17	a, b, c, d, e, f, g, and x represent the atomic ratios of the
18	respective elements, and, when $a=12$, $b=0.1-10$, $c=0.1-20$, $d=2-20$
19	e = 0.001 = 10, $f = 0.30$, $g = 0.4$, and x is a numerical value
20	determined by the state of oxidation of the elements other than
21	oxygen